



**General Product Information:**

ROXUL® products are mineral wool fibre insulations made from basalt rock and slag. This combination results in a non-combustible product with a melting point of approximately 2150°F (1177°C), which gives it excellent fire resistance properties. ROXUL mineral wool is a water repellent yet vapour permeable material.

**Description & Common Applications:**

ROXULPlus® MB is a semi-rigid mineral wool blanket insulation that is lightweight, water repellent, fire resistant and sound absorbent. This product is suited for applications requiring a degree of site durability and ease of installation. ROXULPlus MB is ideal for steel buildings, mechanical equipment isolation and insulation as well as acoustic assemblies. The ROXULPlus MB maximum recommended application temperature is 232°C (450°F).

**Compliance and Performance:**

ASTM C553	Standard Specification for Mineral Fiber Blanket Thermal Insulation for Commercial and Industrial Applications	Type I, II, III
-----------	--	-----------------

**Fire Performance:**

CAN/ULC S102	Surface Burning Characteristics	Flame Spread = 0 Smoke Developed = 0
ASTM E 84(UL 723)	Surface Burning Characteristics	Flame Spread = 0 Smoke Developed = 5
CAN4-S114	Determination of Non-Combustibility	Non-Combustible

**Dimensional Stability:**

ASTM C 356	Linear Shrinkage	0.74 % @ 450°F (232°C)
------------	------------------	------------------------

**Moisture Resistance:**

ASTM C 1104	Water Vapor Sorption	0.028%
-------------	----------------------	--------

**Thermal Resistance:**

ASTM C 518 (C 177)	R-value/inch @ 75°F RSI value/25.4 mm @ 24°C	4.0 hr.ft <sup>2</sup> .F/Btu*** 0.71 m <sup>2</sup> K/W
--------------------	---	---

**Corrosive Resistance:**

ASTM C 665	Corrosiveness to Steel	Pass
ASTM C 795 ****	Stainless Steel Stress Corrosion Specification as per Test Methods C871 and C692: U.S. Nuclear Regulatory Commission, Reg. Guide #1.36: U.S. Military Specifications MIL-I-24244 (all versions including B and C)	Conforms

**Acoustical Performance**

ASTM C423 CO-EFFICIENTS AT FREQUENCIES							
Thickness	125 Hz	250 Hz	500 Hz	1000 Hz	2000 Hz	4000 Hz	NRC
2.5"	0.34	0.76	1.12	1.05	1.04	1.04	1.00
3.5"	0.56	0.99	1.17	1.04	1.05	1.05	1.05
6.0"	1.17	1.20	1.16	1.08	1.08	1.07	1.15



**Density:**

ASTM C 612-00 Actual      2.0 lbs/ft<sup>3</sup>      32 kg/m<sup>3</sup>

**Maximum Recommended Use Temperature:**

ASTM C 411      450°F (232°C)

**Dimensions:**

24" (width) x 48" (length)  
610 mm (width) x 1219 mm (length)

**Thickness:**

Product thickness is available in 2" through 4" in 1/2" increments, as well as 5" and 6" offerings.

**Key Application Qualifiers:**

- Easily cut
- Non-combustible
- Excellent sound absorbency
- Chemically inert
- Does not rot or sustain vermin
- Does not promote growth of fungi or mildew
- Low moisture sorption
- Water resistant
- CFC and HCFC free product and process
- Made from natural & recycled materials



**Other ROXUL Products:**

Please consult ROXUL for all your insulation needs. We have an extensive range of products for all applications from pipe insulation to commercial products to residential batts. ROXUL invites all inquiries and will act promptly to service all of your requirements.

\*\*\*\* "Provisions for lot testing may be required, consult manufacturer."

**Note:**

As ROXUL Inc. has no control over installation design and workmanship, accessory materials or application conditions, ROXUL Inc. does not warranty the performance or results of any installation containing ROXUL Inc's. products. ROXUL Inc's. overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty is in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose.

METRO SUPPLY COMPANY      888-75-METRO  
TWELVE ANDREWS DRIVE      www.MetroSupplyCompany.com  
WOODLAND PARK, NJ 07424