

Technical Product Information

Description & Common Applications:

ROXUL ConRock® is a board insulation product designed

specifically for application in sandwich panel systems where

excellent thermal and fire resistance properties are required.

in panel applications. The product does not encourage the

This rigid board has excellent acoustical dampening properties

and is dimensionally stable which makes it ideal for installation



growth of fungi, molds or bacteria.

BOARD INSULATION 15080* 072113** STRUCTURAL PANELS 06 12 00** STRUCTURAL FRAMING 05 12 00** WALL PANELS 07 42 00** FABRICATED ENGINEERED STRUCTURES 13 34 00**

General Product Information:

ROXUL® products are mineral wool fibre insulations made from basalt rock and slag. This combination results in a noncombustible product with a melting point of approximately 2150°F (1177°C), which gives it excellent fire resistance properties. ROXUL mineral wool is a water repellent yet vapour permeable material.

Compliance and Performance:

ASTM C 612 Mineral Fiber Block and Board Thermal Insulation Type IVA, Complies ASTM E 84 (UL723) Surface Burning Characteristics Flame Spread = 0 Smoke Developed = 5CAN/ULC S102 Surface Burning Characteristics Flame Spread = 0 Smoke Developed = 10 ASTM E 136 Behavior of Materials at 750°C (1382°F) Non-Combustible CAN4 S114 Non-Combustible Test for Non-Combustibility **Moisture Resistance:** ASTM C 1104 Moisture Sorption 0.05% **Dimensional Stability:** ASTM C 356 Linear Shrinkage 0.19% Thermal Resistance: ASTM C 518 (C 177) R-value/inch @ 75°F 4.0 hr.ft².F/Btu RSI value/25.4 mm @ 24°C 0.71 m²K/W **Corrosion Resistance:** ASTM C 665 Corrosiveness Passed ASTM C 795 **** Stainless Steel Stress Corrosion Specification as per Test Conforms Methods C871 and C692: U.S. Nuclear Regulatory Commission, Reg. Guide #1.36: U.S. Military Specifications MIL-I-24244 (all versions including B and C) **Density: Key Application Qualifiers:** 136 kg/m³ 8.5 lbs/ft Fire resistant · Dimensionally (thermally) stable **Compressive Strength** · High impact resistance ASTM C 165 at 10% 4" Board: 6.64 psi (45.8 kPa) Low moisture sorption Excellent sound properties Excellent thermal resistance Dimensions: Does not off gas For details on sizing, please contact our customer service representatives Non-corrosive Chemically inert Other ROXUL Products: Cost effective Please consult ROXUL for all your insulation needs. We have an HCFC free product and process extensive range of products for all applications from pipe insulation Made from natural & recycled materials to commercial products to residential batts. ROXUL invites all inquiries

**** "Provisions for lot testing may be required, consult manufacturer." Note:

and will act promptly to service all of your requirements.

As ROXUL Inc. has no control over installation design and workmanship, accessory materials or application conditions, ROXUL Inc. does not warranty the performance or results of any installation containing ROXUL Inc's. products. ROXUL Inc's. overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty is in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose.

*MASTER FORMAT 1995 EDITION **MASTER FORMAT 2004 EDITION